



CODE 0.503.

aedilia

Washable emulsion paint

GENERAL PROPERTIES

AEDILIA is an emulsion paint devised on innovative criteria which offers good qualities in general & an effortless application.

It offers an optimum "whiteness", good hiding power & washability. The special synthetic polymers in emulsion provide a good scrub resistance, ease of application & flow.

These features together with an appealing satiny effect make AEDILIA a quality finish for interiors.

INSTRUCTIONS

Substrate preparation:

- Bare interior walls: use a soft brush to remove dust & unsound plaster. Level any imperfections with LITOSTUCCO 1.050.1010 or SILVER STUCK 1.963.1010 adding as many times as necessary. Allow 6 hrs, sand the stuccowork & clean accurately. Seal the whole surface with a hand of ISOLEX W or ARDFIX thinned (1 part in 8 parts of water). Allow 4 or 12 hrs respectively & apply 2 hands of AEDILIA.
- Interiors with distemper paintwork: clean accurately & stucco any imperfections with LITOSTUCCO as indicated above. Sand, seal the whole surface with a hand of ISOLEX W or ARDFIX. Allow 12 hrs & apply AEDILIA.
- Interiors with washable emulsion paintwork: clean accurately, stucco any imperfections, sand & dust. Seal the stucco work with a hand of ISOLEX W or ARDFIX. Allow 4 hrs & proceed with AEDILIA.

Application:

Apply AEDILIA as follows:

- Brush: stir well, dilute at 30-40% in water volume & apply by cross brushing. Allow 2-3 hrs & proceed with the second hand thinning AEDILIA at 30-35% in water volume.
- Roller: dilute at 15-20% in water volume.
- Air-spray gun: thin at 10-15% in water volume until roughly 80 DIN/sec viscosity (DIN cup # 4 at 20°C) and apply using 1,5-1,9 mm Ø nozzles - pressure around 3 kg/cm. Allow at least 6 hours between each layer.

- AEDILIA is easy to tint using IDROPAINTE 502, high concentration colorants COLORATUTTO 0.951 & ARDCOLOR 2.950.
- Store in cool, frost free, premises. Do not apply at a temperature below +5°C or above +35°C.
- Wash equipment immediately after use with water.
- AEDILIA is compatible with the 16COLOURS & WIZARD tinting systems.
- Use products in compliance with the current Health & Safety Regulations. Dispose of spent material/containers according to the same.
- Refer to the PSDS for further details.

TECHNICAL PROPERTIES

SPECIFIC WEIGHT		1560 ÷ 50 g/l
VISCOSITY AT 20 °C		15000 ± 2000 cp
COLOUR		White
DRYING AT 20 °C	TOUCH DRY	2 hrs
	THROUGH DRYING	24 hrs
WET SCRUB RESISTANCE	EN 13300 (ISO 11998)	Class 3
CONTRAST RATION	EN 13300 (ISO 6504-3)	Class 1 to 5 m²/l
GLOSS (85°)	EN 13300 (EN ISO 2813)	< 10 G.U. Matt

YIELD

A two coat cycle implies a yield of 5,5 - 6 m²/l.

TENDER SPECIFICATION ITEM

WASHABLE EMULSION PAINT

Application on treated surfaces of two layers of highly covering emulsion paint based on synthetic copolymers in aqueous dispersion & colouring pigments type AEDILIA, with a min consumption of 0,18 l/m².

€/m²

The data herein were correct at the time of Quality Control & refer to standardized environmental conditions. The same are to be considered as a guide.

Revision 2024/02



ard raccanello s.p.a.

35129 PADOVA – Zona Ind.le Nord 1^a Strada, 13 – Tel. 049.8060000 (5 linee)
Fax 049.773749 – www.ard-raccanello.it - E-mail: assistenza@ard-raccanello.it