



**CODE 0.506.**

## **maison**

**Super washable latex paint for interiors & exteriors**

---

### **GENERAL PROPERTIES**

MAISON is a high performing wall paint which offers optimum wash resistance, refinishing, covering power, whiteness & water vapour permeability.

MAISON flows perfectly so it is easy to apply & offers a refined velvety matt effect.

MAISON is an extremely versatile product devised for painting two coat plaster work, precast panels, plaster of Paris & plasterboard.

EPD® Certification, Environmental Product Declaration in accordance with ISO 14025 and EN 15804.

### **INSTRUCTIONS**

#### **Substrate preparation:**

- Bare exterior walls: brush thoroughly removing all dust, dirt & unsound plaster. Level big imperfections of the support with ARDPLAN AS/BS. Check that the wall is perfectly dry and apply one layer of ISOLEX W, or ISOLEX ready to use, or one layer of ARDFIX properly diluted ( one part of product in 8 parts of water). Allow 12 or, respectively, 4 hours and apply two layers of 0.506.
- Already painted exterior walls and partially degraded: remove any part of unsound paint and eventual efflorescences; in presence of moulds it is appropriate to perform a treatment with ARDSAN RISANANTE MURALE. Remove thoroughly from dust and dirt and level imperfections with suitable repair mortar; check that the wall is perfectly dry and apply on all surface one layer of ISOLEX W, or ISOLEX or PAINTGUM 7 FONDO COPRENTE in case the surface is dark or the colour is not uniform. Allow 12 hours and apply 2 layers of MAISON
- Bare interior walls: remove dust & unsound plaster with a soft brush. Level imperfections with LITOSTUCCO 1.050.1010 filling as required. Allow 6 hrs, sand the stuccoed areas & clean thoroughly. If the surface is not particularly chalky, apply 2 hands of MAISON directly. Otherwise, pretreat the surface by applying ISOLEX W or ARDIFX -thinning according to the conditions of the substrate -.
- Interior surfaces with washable latex paintwork: clean thoroughly, stuccoing eventual imperfections, sand & remove dust. Seal the stuccoed areas with a layer of ARDFIX. Allow 4 hrs and proceed with MAISON.

## Application:

Apply MAISON as follows:

- Brush: stir well, dilute at 35-40% in water volume. Stir again thoroughly & apply in a criss-cross fashion. Allow 3 hrs & proceed with the second hand diluting at 30-35% in water volume.
- Roller: dilute at 25-30% in water volume. Roller application is recommended when using medium or dark hues. Do not thin above 20% when applying on plaster of Paris or plasterboard.
- Air-spray gun: thin at 10-15% in water volume until roughly 80 DIN/sec viscosity (DIN cup # 4 at 20°C) and apply using 1,5-1,9 mm Ø nozzles - pressure around 3 kg/cm. Allow at least 6 hours between each layer.
- MAISON is compatible with the 16 COLOURS & WIZARD tinting systems.
- Do not apply at ambient or substrate temperature below +5°C or above +35°C.
- Wash equipment immediately after use with water.
- Store in cool, frost free premises.
- Use in compliance with the current Health & Safety Regulations. Dispose of spent material/containers according to the same.
- Refer to the PSDS for further information.

## TECHNICAL PROPERTIES

SPECIFIC WEIGHT		<b>1580 ± 50 g/l</b>
VISCOSITY AT 20°C		<b>12.000 ± 1500 cP</b>
COLOUR		<b>White</b>
DRYING AT 20 °C	TOUCH DRYING	<b>24 hrs</b>
	THROUGH DRYING	<b>2 hrs</b>
WATER VAPOUR PERMEABILITY	EN ISO 7783-1&2	<b>Class V' (high)</b>
WET SCRUB RESISTANCE	EN 13300 (ISO 11998)	<b>Class 2</b>
CONTRAST RATION	EN 13300 (ISO 6504-3)	<b>Class 2 to 6 m<sup>2</sup>/l</b>
GLOSS (85°)	EN 13300 (EN ISO 2813)	<b>&lt; 5 G.U. Dead Matt</b>

## YIELD

A two ply cycle implies a yield of about 7 m<sup>2</sup>/l. Such yield refers to smooth surfaces with medium absorption. However, it is best to determine the same by testing.

## TENDER SPECIFICATION ITEM

### SUPER WASHABLE LATEX PAINT FOR INT/EXT

A two layer application on prepared surfaces of a super washable latex paint for interiors & exteriors type MAISON with a minimum consumption of 0,14 l/m<sup>2</sup>.

€/m<sup>2</sup>

The data herein were correct at the time of Quality Control and refer to standardized environmental conditions. The same are to be considered as a guide.  
Revision 2024/02



ard raccanello s.p.a.

35129 PADOVA – Zona Ind.le Nord 1ª Strada, 13 – Tel. 049.8060000 (5 linee)  
Fax 049.773749 – www.ard-raccanello.it - E-mail: assistenza@ard-raccanello.it