



CODE 1.630

## intonaclima 1,5 mm

Algae resistant acryl-siloxane rustic coating

### GENERAL PROPERTIES

INTONACLIMA 1,5 mm is an acryl-siloxane coating for exteriors.

The product lends a remarkable resistance to atmospheric agents & alkali, optimum adherence, applicability, working & low dirt pick-up. The light-fast pigments guarantee a good colour retention even on walls exposed to radiation & weather extremes. It also contains specific additives which inhibit algae & mould growth.

INTONACLIMA 1,5 mm is ideal on urban buildings in two coat plaster work, cement mortar renders (whether or not finished), gypsum plaster for interiors & smooth compact prefabricated concrete structures.

INTONACLIMA 1,5 mm is specific for the finishing of ETICS.

### INSTRUCTIONS

#### Substrate preparation:

- Bare surfaces: ensure the substrate has weathered for at least 28 days. Clean thoroughly & remove any unsound paintwork. Ensure the wall is perfectly dry & apply a hand of ISOLEX W, ISOLEX or a layer of ARDFIX suitably diluted (1 part of product in 8 parts of water). Allow 12 & 4 hrs respectively, level any imperfections (holes, cracks etc) with ARDPLAN AS/BS. Apply a layer of RASANTE A PENNELLO on smooth &/or poor absorbing surfaces in order to achieve the desired result. Allow at least 6 hrs and apply INTONACLIMA 1,5 mm.
- Unsound painted surfaces: remove any unsound paintwork and efflorescence. Treat mould with ARDSAN RISANANTE MURALE 0.916. Clean thoroughly, ensure the wall is perfectly dry and fix the surface with a hand of ISOLEX W or ISOLEX. Allow 12 hrs, stucco the large imperfections (holes, cracks etc.) with ARDPLAN AS/BS & apply INTONACLIMA 1,5 mm.
- Surfaces with unsound plastic coatings/embossed plaster: remove any unsound paintwork & efflorescence. Treat mould with ARDSAN RISANANTE MURALE. Clean thoroughly and seal the whole surface with a layer of ISOLEX W or ISOLEX. Allow 12 hrs, accurately level the whole surface and apply INTONACLIMA 1,5 mm.

- When finishing products with limited covering power are employed we suggest using PRIMER RIEMPITIVO COPRENTE (refer to the formulary for shades). RASANTE A PENNELLO is preferable for slightly rough surfaces.

#### Application:

- INTONACLIMA 1,5 mm is ready for use and does not require thinning. Stir well until homogeneous & apply the first coat using a steel or plastic float. Allow 12 hrs & apply a second hand; before the product “films”, use a trowel to smooth the surface.
- Do not apply at ambient/substrate temperatures below + 5°C or above 35°C & R H above 75%. Avoid applying during cold & damp periods, in direct sunlight or strong wind.
- After application, exterior surfaces must be protected against rain until perfectly dry, usually after 48 hrs at 20° C.
- Wash equipment immediately after use with water.
- Walls with efflorescence or subject to rising damp must be restored before application in order to guarantee adherence.
- When different batches are used, we recommend mixing the products accurately to avoid differences in shades.
- When applying on extensive surfaces apply “wet-on-wet” to avoid shadowing.
- Store in cool premises, under frost proof conditions.
- Use in compliance with the current Health & Safety regulations. Dispose of spent material/containers according to the same.
- INTONACLIMA 1,5 mm can be tinted with the 16COLOURS & WIZARD tinting systems’ pastes.
- Refer to the PSDS for further details.

#### TECHNICAL PROPERTIES

NATURE OF BINDER	Acryl siloxanic polymers		
COLOUR	White & tinting system hues		
MASS VOLUME	1800 – 1900 g/l		
DYNAMIC VISCOSITY	160.000 ± 200.000 cP		
UV RESISTANCE	Sup. 3 <sup>rd</sup> grade Grey scale		
ALKALI RESISTANCE	No structural/chromatic variation		
DRYING AT 20°C	TOUCH DRY		4 hrs
	THROUGH DRYING		48 hrs
PERMEABILITY (WATER VAPOUR)	EN ISO 7783-1 & 2	S <sub>d</sub>	0,342 m
		Class	V <sub>2</sub> (average)
CAPILLARY ABSORPTION & WATER PERMEABILITY	EN1062-3	w	0,067 kg/m <sup>2</sup> √t
		Class	W <sub>3</sub> (low)
ADHESION FOR DIRECT TRACTION	EN 1542	RESULT	Complies (adhesion ≥ 0,3 Mpa)
DURABILITY	EN 13687-3	RESULT	Complies (adhesion ≥ 0,3 Mpa)
THERMAL CONDUCTIVITY	EN 1745	λ <sub>10</sub> DRY [W/MK]	1,060
FLASH POINT	EN 13501-1		Class C
HAZARDOUS SUBSTANCES		RESULT	Complies

*In compliance with the UNI EN 15824 CE Marking*

#### YIELD

Once dry the coating is about 1,5 mm thick. If applied correctly without spilling the average yield is 0,36 m<sup>2</sup>/kg. Said yield refers to smooth substrates with medium absorption. We recommend testing on the specific substrate.

---

**TENDER  
SPECIFICATION ITEM**

**ALGAE RESISTANT ACRYLIC-SILOXANE RUSTIC COATING**

Float application on pretreated surfaces of a smooth rustic pigmented coating based on binders in aqueous dispersion, coloured pigments & mineral chargers of various granulometries – which after drying produces a 1,5 mm thick coating - INTONACLIMA 1,5mm - with a min consumption of 2,8 kg/m<sup>2</sup>.

€/m<sup>2</sup>

---

The data herein were correct at the time of Quality Control and refer to standardized environmental conditions.  
The same are to be considered as a guide.  
*Revision 2015/06*



ard raccanello s.p.a.

35129 PADOVA – Zona Ind.le Nord 1ª Strada, 13 – Tel. 049.8060000 (5 linee)  
Fax 049.773749 – [www.ard-raccanello.it](http://www.ard-raccanello.it) - E-mail: [assistenza@ard-raccanello.it](mailto:assistenza@ard-raccanello.it)